

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶:B05B 5/08, A61K 9/28, A61J 3/00, B05D
1/06

A1

(11) International Publication Number:

WO 96/35516

(43) International Publication Date: 14 November 1996 (14.11.96)

(21) International Application Number: PCT/GB96/01102

(22) International Filing Date: 8 May 1996 (08.05.96)

(30) Priority Data:

9509347.2

9 May 1995 (09.05.95)

GB

9520302.2

5 October 1995 (05.10.95)

GB

(71) Applicant (for all designated States except GB US): BERWIND
PHARMACEUTICAL SERVICES, INC. [US/US]; Moyer
Boulevard, West Point, Pennsylvania, PA 19486 (US).(71) Applicant (for GB only): BPSI HOLDINGS, INC. [US/US];
Suite 1300, 1105 North Market Street, P.O. Box 8985,
Wilmington, DE 19899-8985 (US).

(72) Inventors; and


(75) Inventors/Applicants (for US only): HOGAN, John, E.
[GB/GB]; The Lodge, Upper St. Anne's Road, Faversham,
Kent ME13 8SY (GB). STANFORTH, John, Nicholas
[GB/GB]; High Trees, 170 Bloomfield Road, Bath BA2
2AT (GB). REEVES, Linda [GB/GB]; 6 Magdalen Road,
Bath BA2 4QA (GB). PAGE, Trevor [GB/GB]; Bellepais,
Lime Walk, Southampton, Hampshire SO4 5AR (GB).(74) Agent: MARLOW, Nicholas, Simon; Reddie & Grose, 16
Theobalds Road, London WC1X 8PL (GB).(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY,
CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS,
JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD,
MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD,
SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN,
ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent
(AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent
(AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU,
MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, ML, MR, NE, SN, TD, TG).

Published

With international search report.

Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.

(54) Title: ELECTROSTATIC COATING



(57) Abstract

The invention provides apparatus for electrostatically coating a pharmaceutical tablet core with powdered coating material. The apparatus comprises a first rotary drum (12) on which a core is held in electrical isolation from its surroundings but at a potential difference to earth by an electrode which contacts the core. The core is carried past a coating station B at which particles of powder having an opposite potential difference to earth are held in a tray (18). The surface of the drum is held at the same potential difference to earth as the powder particles. The powder is attracted to the core, and not to the drum, coating the exposed surface of the core. The drum carries the coated core past a fusing station C at which a heater fuses the powder to form a continuous film coating. The core is then turned and transferred onto a second drum (12') where the other surface is coated in the same way.

ELECTROSTATIC COATING

The present invention relates to a method and apparatus for the electrostatic coating of electrically poorly conducting substrates. It finds particular application in the coating of solid pharmaceutical dosage forms such as tablet cores, capsules, granules and beads with particulate coating materials, including powders and droplets of liquid.

The use of electrostatic techniques to coat electrically conductive substrates, such as metal objects, is well known and successful. The coating, such as droplets of liquid paint, is electrically charged by applying a potential difference to it and is attracted to the earthed substrate.

The conventional electrostatic coating technique described above has not been successfully applied to the coating of pharmaceutical tablet cores or other poor electrical conductors, generally those with a resistivity of more than $10^{10} - 10^{15}$ Ωm . Proposals have been made in which tablet cores are earthed, and a powdered coating material is directed at them through a nozzle which imparts an electrical charge to the powder. The powder coating is then fused to give a uniform coat. This method has been found inefficient, since adequate earthing of the cores has not been achieved, and the charge on the powder accumulates on the surface of the cores, repelling further charged powder. Even if the cores are carried on for example an earthed conveyor belt, the poorly conducting nature of the cores allows charge to build up.

Further, the bulk of the powder (95% in the case of corona charging) is uncharged, and does not land or stay on the cores, and must either be recovered or wasted. These difficulties lead to non-uniformity in the weight and thickness of the coating applied to the cores. This is pharmaceutically unacceptable, in particular when the core coating plays a significant role in the

timing of the release of the pharmaceutical into the body after ingestion.

Improvements have been proposed, for example in WO 92/14451 which proposes moistening the cores with water prior to spraying with the charged powder, to improve the earthing of the surfaces of the cores and to encourage the powder, once on the surfaces, to remain. Even with these improvements, coating remains inherently inefficient; powder is wasted and the time necessary for complete coating is too long for efficient production.

The present invention overcomes these problems by providing in accordance with a first aspect a method for electrostatically coating an electrically poorly conducting substrate comprising bringing the substrate to a coating station at which it is held electrically isolated from, and preferably at a potential difference to, its surroundings adjacent a source of particulate coating material, the substrate and the coating material being held at a potential difference to each other sufficient to coat the exposed surface of the substrate with particles of coating material. Preferably, the substrate is held at a potential difference to earth.

It is particularly preferred that the electric field between the coating material and the substrate is shaped. The field can be shaped so that the substrate is in a potential well. That is, the substrate is surrounded by a potential difference to earth different to its own, there being a sharp cut-off between the two potential differences. Thus, substantially all the coating material is attracted to the substrate, reducing waste of the coating material and avoiding the problems associated with coating material falling on the substrate surroundings.

Shaping of the field is achieved by manipulation of the potential difference between the substrate, its surroundings and the coating material. For example, a substrate is carried by but insulated from a surface, the surface being held at the same

potential difference to earth as the coating material while the substrate is held at a different potential difference to earth to that of the coating material. Coating material is therefore attracted to the substrate and not to the surface.

Preferably, substantially the only motive force between the substrate and the coating material is electrostatic. It may be desirable to provide particulate coating material in the form of a cloud of particles, formed for example by fluidising a bed of the coating material. Also preferably, the substrate is supported on an electrode while being electrically isolated from its surroundings.

For powder coating applications, the substrate may be brought to a pretreatment station at which the exposed surface of the substrate is coated with a capture-enhancing liquid. After coating with the coating material, the substrate can be brought to a heating station where the coating material if powder is fused or if liquid is dried to an effectively continuous uniform coating. The reverse surfaces of the substrate can then be coated in the same way with the same coating material as the first-coated surface or with a different material. In this way, for example bi-coloured coated substrates may be produced. Preferably, the method is carried out continuously.

It is preferred that powders used in the method according to the invention has a resistivity greater than $10^8 \Omega m$, preferably between 10^8 and $10^{15} \Omega m$.

There is provided in accordance with a second aspect of the invention apparatus for electrostatically coating an electrically poorly conducting substrate comprising a coating station at which the substrate is substantially electrically isolated from, and preferably at a potential difference to, its surroundings adjacent means for supplying a particulate coating material, and means for holding a substrate and a coating material at a potential difference to each other. Preferably, the substrate is held at a potential difference to earth.

Preferably, the apparatus further comprises an electric field shaping device adjacent the substrate. Particularly preferably, the electric field shaping device surrounds the substrate.

The apparatus advantageously includes an electrically conductive support surface such as a drum electrically isolated from the substrate which carries the substrate at least at the coating station. A field shaping device can be provided by provision for the support surface to be held at a potential difference to earth having the same sign as the potential difference to earth of the coating material.

In the case of powder coatings, the apparatus can include a pretreatment station for supplying capture-enhancing liquid to the exposed surface of a substrate and a conveyor for conveying the substrate between the pretreatment station and the coating station, the pretreatment station being upstream of the coating station. The conveyor is preferably a drum. The apparatus preferably includes a heating station downstream of the coating station for fusing the powder or drying the liquid coating material on the substrate to a film.

. In a third aspect, the invention provides a drum for the preferred apparatus of the invention.

In a fourth aspect, the invention provides a coated pharmaceutical having one coating on one face and a different coating, or no coating, on the other face. The coatings may be of different colours or of different polymers or biologically active materials.

The source of particulate coating material, whether powder or liquid, may be a multiple source comprising several sub-sources. The sub-sources can be of different colour coating materials or of coating materials containing different polymers. Thus, tablets having more than one colour on a single surface can be provided. The faces can be bicoloured or striped. Similarly, a tablet can carry two or more different polymer

coatings, side by side.

In a fifth aspect, the invention provides a coated pharmaceutical the surface of at least one face of which is two or more adjacent different coatings. The coatings may be of different colours or of different polymer composition.

The substrate, such as the core of a pharmaceutical tablet, may be completely electrically isolated from its surroundings, for example in free fall. Preferably, however, while coating takes place the substrate is in contact with an electrode through which it is maintained at a potential difference to earth (and to its surroundings). If the substrate is held on a support surface, such as the surface of a drum, it may sit in a depression in the surface. The surface of the depression can be of a conductive material and form part of the electrode. The support surface may be surrounded by an arrangement of insulating, conducting or semiconducting areas which act to shape the electrical field pattern. The substrate is thus surrounded by a potential well, to ensure that charged particles of coating material are attracted to it, rather than to the surroundings, including the support surface, if any, carrying the substrate.

The invention will be further described, by way of example, with reference to the drawings, in which:

Figure 1 shows schematically a preferred embodiment of apparatus according to the invention;

Figure 2 shows diagrammatically a cross-section of a drum of the apparatus of Figure 1; and

Figure 3 shows diagrammatically means for providing droplets of liquid coating material for an apparatus according to the invention.

The apparatus shown schematically in Figure 1 is for coating both sides of pharmaceutical tablet cores. The apparatus comprises an inclined tablet core feed chute 10 leading to a first rotatable drum 12. The drum 12 is of plastic with a steel surface and has circular depressions 14 (Figure 2) in its outer

surface in each of which a core can be held by vacuum, as will be explained later.

The drum 12 is rotatable in the direction shown by the arrow in Figure 1. Adjacent the circumference of the drum 12 downstream of the tablet feed chute 10 is a pre-conditioning station A comprising an electrostatic spray gun 16, which produces charged droplets which are attracted to the substrate cores on the drum by reason of the potential difference between the droplets and the cores. Downstream of the preconditioning station A is a coating station B comprising a vibrating powder tray 18 for holding, fluidising and re-circulating the powder with which the cores are to be coated. Downstream of the coating station is a fusing station C comprising a heater 20. After the fusing station C, the coated core passes a cooling station, not shown, where cool air is directed over or around the core to cool the fused coating.

A second drum 12' is adjacent the first drum 12, the nip between the drums being downstream of the fusing station C and the cooling station. The second drum 12' rotates in the opposite sense to the first drum 12, as indicated by the arrow in Figure 1.

The second drum 12' is provided with a preconditioning station A' comprising a gun 16', a coating station B' comprising a powder tray 18', a fusing station C' comprising a heater 20' and a cooling station (not shown).

A core collection chute 22 inclines away from the second drum 12' downstream of the fusing station C', taking coated cores to be further processed and packed.

The first drum 12 will be described in more detail with reference to Figure 2. It comprises a rotatable shell 24, the outer face of which carries the depressions 14. In Figure 2, only five exemplary depressions 14 are shown; it will be appreciated that in practice there will usually be more depressions, evenly spaced in a circumferential row around the shell 24, and that there may be several circumferential rows across the width of the

drum, whether formed by one continuous shell or several contiguous shells. The depressions 14 on the drums are shaped and dimensioned to ensure that the complete face of the core and half the depth of the side wall is coated while the core is on one drum. In the case of a circular tablet core, a depression diameter close to that of the core diameter is preferred. In some applications, the depth of the depression should be such as to allow at least 50% of the core thickness to be exposed to the particles of the coating material so that exposure of first one face of the core and then the other leads to complete coverage of the core.

The surface of each depression 14 is electrically insulated from the surfaces of other depressions on the drum and is provided with a pick up arm 26 extending radially inward, toward but ending short of the centre of the drum. The pick up arms 26 are attached to the inner surface of the shell 24 and rotate with it.

The pick up arm 26 and the depression 14 together make a moving electrode to charge a core in a depression. Each depression 14 has means for holding the core against forces such as gravity, for example a passage 28 through its wall which can be in communication with a vacuum manifold 30 which extends around a portion of the periphery of the drum interior from immediately upstream of the core feed chute 10 to adjacent the nip between the first drum 12 and the second drum 12'.

A first, earthed, stationary arcuate electrode 32 is located inside the drum at an angular position corresponding to the preconditioning station A. A second stationary arcuate electrode 34 at a potential difference to earth is located inside the drum at an angular position corresponding to the coating station B. The outer arcuate surfaces of the stationary electrodes are at the same radial distance from the centre of the drum as the free ends of the pick up arms 26 of the moving electrodes. As the shell 24 rotates, the moving electrodes contact the first and second stationary electrodes sequentially.

The drum 12 is held at a potential difference to earth having the same sign as the potential difference to earth of the coating powder.

The second drum 12' is constructed similarly to the first drum, comprising a rotatable shell with depressions, pick up arms, first and second stationary electrodes and a vacuum manifold. The angular locations of the first and second stationary electrodes correspond to the second preconditioning station A' and the second coating station B', and the vacuum manifold extends from immediately upstream of the nip between the two drums to adjacent the core collection chute 22.

In use, cores are fed continuously to the core feed chute 10. A core passes down the core feed chute 10 into a depression 14 in the rotating shell 24 of the first drum 12. At that angular position, the depression overlies the vacuum manifold 30, and so the core is held in the depression by the vacuum through the passage 28 in the shell. The shell 24 continues to rotate bringing the core to the preconditioning station A, at which point the pick up arm 26 attached to the depression 14 contacts the first stationary electrode 32, earthing the moving electrode and thus the core held in the depression. As the earthed tablet core passes the electrostatic spray gun 16, its exposed surface is sprayed with charged droplets of a capture-enhancing liquid, for example polyethylene glycol.

The shell 24 continues to rotate, taking the moving electrode 26 out of contact with the first stationary electrode 32 and bringing it into contact with the second stationary electrode 34, as the tablet core approaches the coating station B. The exposed polyethylene glycol treated core surface is now at a potential difference to earth, and coating powder is attracted to it from the powder tray 18. The potential well generated by holding the surface of the drum and the powder at the same potential difference to earth as each other and the core at a different potential difference to earth ensures that powder is

attracted substantially only to the core and that the surface of the drum remains substantially free of powder.

The shell 24 continues to rotate, taking the moving electrode 26 out of contact with the second stationary electrode 34 and bringing the core to the fusing station C, where the heater 20 fuses the powder on the coated surface of the core to form an effectively continuous film.

As the shell 24 continues to rotate, the core leaves the fusing station C, passes through the cooling station (not shown), so that the depression carrying the core no longer overlies the vacuum manifold 30. The core drops from the first drum 12 into a depression on the outer surface of the second drum 12', with its uncoated surface uppermost; the depression is in communication with the vacuum manifold of the second drum. The coating of the core is completed as it travels past the second preconditioning A', coating B' and fusing C' stations. The coating powder at the second coating station may be the same as that at the first, or different. Thus, tablets having differently coated surfaces can be produced. Such dissimilar coatings can be used to provide functionally modified behaviour such as altered diffusion or dissolution controlled drug release or cosmetically different coatings such as those which would produce a bicoloured tablet. As the coated tablet draws adjacent the collection chute 22, the depression carrying it ceases to overlie the vacuum manifold, and the tablet falls into the chute and is further processed and packed.

The drums themselves are preferably at least 60 mm in diameter and not less than the minimum tablet diameter in width, rotating at least $\frac{1}{4}$ r.p.m. The pressure in the vacuum manifold is sufficiently low to hold the tablet against gravity, preferably between 0.2 and 0.6 bar absolute.

In the electrostatic spray guns 16,16' at the preconditioning stations A,A', a semiconducting, non-volatile fluid, such as polyethylene glycol or an aqueous solution

thereof is fed at a rate of 0.1 to 1 ml/min. to a steel capillary of internal diameter 0.05 to 2 mm. The capillary is connected to a current limited high voltage (up to 50 kV at 30 to 100 μ A) potential difference to earth as each core on a drum passes the gun, and a mist of charged droplets is discharged from the capillary toward the core on the drum; since the cores on the drums are earthed at the preconditioning stations, the charged droplets are guided by the electric field between the capillary and the core to the exposed surface of the core, where they are captured. The cores may be held at a potential difference to earth at the preconditioning stations, providing that they are also at a potential difference to the capillaries. In this case, the first stationary arcuate electrode 32 is at a potential difference to earth. The supply of droplets from each capillary is controlled by switching the voltage off and earthing the capillary through a resistor (1 to 10 M Ω) as each core leaves the preconditioning station; this ensures a sharp cut off of the droplets between tablet cores.

The pre-conditioning step may not always be required.

At coating stations B,B', powdered coating material is supplied by vibrating feeders to the vibrating trays 18,18'. The level of the powder in the trays is determined by a levelling blade above each tray. The powder may be vibrofluidized and continuously recirculated. The trays may be of a plastics material having an earthed metal strip under the arc swept by the tablet cores on the respective drums or they may be metallic trays. An alternative way to charge the particles is triboelectrical charging. The trays are preferably 50 to 150 mm long and 3 to 40 mm wide. If more than one tray is used, to provide a bi- or multicoloured face or a face carrying more than one polymer composition, the tray dimensions will be appropriately different. The tablet cores are charged by a voltage of -3 to -15 kV current limited to 5 μ A.

A preferred powder coating composition is:

46.5% by weight Eudragit RS ammonio-methacrylate
co-polymer
28.0% by weight Klucel hydroxy propyl cellulose
15.0% by weight titanium dioxide
5.0% by weight aluminium lake
5.0% by weight polyethylene glycol 6000
0.5% by weight Aerosil 200 colloidal silicon dioxide

Another preferred powder coating composition is:

39.75% by weight Eudragit RS ammonio-methacrylate
co-polymer
39.75% by weight Klucel (hydroxypropylcellulose)
15.0% by weight Titanium dioxide
5.0% by weight Aluminium lake
0.5% by weight Aerosil (colloidal silicon dioxide)

The components are premixed under high shear, then wet granulated by mixing under high shear with water (10-15% by weight). The granulated mixture is dried in fluid bed drier at about 45°C for 20 to 30 minutes to reduce the moisture content to below 3% by weight. The dried granules are milled and micronised to a powder having a size distribution such that 50% by volume of the particles are of a size less than 20 μ m, and about 100% by volume are of a size less than 60 μ m. The peak size is about 10 μ m.

If the particulate coating material is liquid droplets, the apparatus is of a similar construction to that for applying powdered coating material to the cores. The vibrating trays holding the powder are replaced by means for producing liquid droplets with low momentum, such as that shown in Fig. 3. The apparatus may be designed so that a source of powder coating material may be easily replaced by a source of droplets of liquid coating material.

Droplets are produced by a spray gun 41 held at earth potential and electrically connected to the drum (12). The gun may be formed of metal or a polymer material. The direction of the spray is towards a baffle 42 down which the coalesced droplets can run into a re-circulating reservoir 43. The spray gun 41 produces a spray of relatively high initial momentum. This impinges on an internal baffle which breaks the spray up into a mist of droplets of low momentum. The momentum of the droplets produced by the spray gun is mainly in a direction normal to the substrate 44. If the substrate is uncharged there will be effectively no droplet capture onto the substrate surface. When the charge is applied to the substrate surface the droplets are attracted thereto to form a coating thereon which is later dried at a drying station similar to the fusing station C of the powder treatment apparatus. The pre-conditioning step A may be omitted in the case of liquid coating material.

A preferred liquid coating composition comprises:

hydroxypropylmethylcellulose	70%
glycerol	7%
iron oxide yellow	23%

in aqueous dispersion.

At the fusing or drying stations C, C', energy is imparted to the core surfaces to fuse the powder or dry the liquid and provide a uniform coating on the exposed surfaces of the core. The energy is provided by focused radiation preferably in the infra-red region; the energy power requirement will be determined largely by the coating material. After fusing or drying, the coating is set by cooling, using an air blower.

Preferred coating apparatus according to the invention can coat up to 300,000 tablet cores each hour.

CLAIMS

1. A method for electrostatically coating an electrically poorly conducting substrate comprising bringing the substrate to a coating station at which it is held substantially electrically isolated from its surroundings adjacent a source of particulate coating material, the substrate and the coating material being held at a potential difference to each other sufficient to coat the exposed surface of the substrate with particles of coating material.
2. A method according to claim 1 in which the substrate is at a potential difference to its surroundings.
3. A method according to claim 1 or 2 in which the electric field between the coating material and the substrate is shaped so that the substrate is in a potential well.
4. A method according to claim 1, 2 or 3 in which at the coating station the substrate is supported by but electrically isolated from an electrically conductive surface.
5. A method according to claim 4 in which the potential difference to earth of the surface and of the coating material are of the same sign.
6. A method according to claim 4 or 5 in which the surface is at the same potential difference to earth as the coating material.
7. A method according to any preceding claim in which the substrate is held at the coating station at a potential difference to earth.
8. A method according to any preceding claim in which substantially the only motive force between the substrate and the

coating material is electrostatic.

9. A method according to any preceding claim in which the substrate is supported, and in electrical contact with an electrode, the substrate being otherwise electrically isolated from its surroundings.

10. A method according to claim 9 in which a plurality of substrates are supported on respective ones of plurality of electrodes electrically isolated from each other and forming part of a support surface.

11. A method according to claim 10 in which the support surface is continuous.

12. A method according to any preceding claim in which the coating material particles are at a potential different to earth.

13. A method according to any preceding claim in which a powdered coating material is used.

14. A method according to claim 13 further comprising bringing the substrate coated with powder to a fusing station where the powder on the substrate is fused to a uniform coating.

15. A method according to claim 14 in which the fusing is by heating.

16. A method according to claim 15 in which the heating is by infra-red radiation.

17. A method according to any of claims 14, 15 and 16 further comprising cooling the fused coating on the substrate.

18. A method according to any of claims 13 to 17 further comprising, prior to bringing the substrate to the coating station, bringing the substrate to a preconditioning station at which the exposed surface of the substrate is coated with a capture-enhancing liquid.
19. A method according to claim 18 in which the coating carried out at the preconditioning station is electrostatic coating.
20. A method according to claim 18 to 19 in which the capture-enhancing liquid is partially conducting.
21. A method according to any of claims 1 to 12 in which the coating material is liquid.
22. A method according to any preceding claim in which the substrate is carried by a support surface having a plurality of individual locations adapted to receive a substrate and hold it electrically isolated from the remainder of the surface and at a predetermined potential difference to earth.
23. A method according to any preceding claim in which the substrate is held in contact with an electrode at least while it is at the coating station.
24. A continuous method according to any preceding claim in which the substrate is carried by the surface of a rotating drum.
25. A method according to any preceding claim further comprising turning the substrate after application of a coating to a first surface of the substrate and applying a coating to a second surface of the substrate.
26. A coated substrate produced by a method according to any of claims 1 to 25.

27. Apparatus for electrostatically coating an electrically poorly conducting substrate comprising a coating station at which a substrate is substantially electrically isolated from its surroundings adjacent means for supplying particulate coating material; and means for holding a substrate and particulate coating material at a potential difference to each other.

28. Apparatus according to claim 27 comprising means for holding a substrate at a potential difference to its surroundings at the coating station.

29. Apparatus according to claim 27 or 28 further comprising an electric field shaping device adjacent the substrate which shapes the field so that the substrate is in a potential well.

30. Apparatus according to claim 29 in which the electric field shaping device surrounds the substrate.

31. Apparatus according to any of claims 27 to 30 further comprising an electrically conductive support surface for, in use, carrying a substrate at least at the coating station such that the substrate is electrically isolated from the support surface.

32. Apparatus according to claim 31 in which the support surface has a plurality of individual locations adapted to receive a substrate and hold it electrically isolated from the remainder of the support surface and at a predetermined potential difference to earth.

33. Apparatus according to claim 31 or 32 in which the potential difference of the support surface to earth and of the coating material to earth are of the same sign.

34. Apparatus according to claim 31, 32 or 33 comprising means for holding the support surface at the same potential difference

to earth as the coating material.

35. Apparatus according to any of claims 27 to 34 comprising means for holding a substrate at the coating station at a potential difference to earth.

36. Apparatus according to any of claims 27 to 34 further comprising a fusing station downstream of the coating station for fusing a powdered coating material on the substrate to a film.

37. Apparatus according to claim 36 in which the fusing station comprises a heater.

38. Apparatus according to claim 37 in which the heater is a source of infra-red radiation.

39. Apparatus according to claim 34, 37 or 38 further comprising a cooling station downstream of the fusing station.

40. Apparatus according to claim 39 in which the cooling station comprises an air blower.

41. Apparatus according to any of claims 27 to 40 further comprising a preconditioning station for supplying capture-enhancing liquid to the exposed surface of a substrate and a conveyor for conveying the substrate between the preconditioning station and the coating station, the preconditioning station being upstream of the coating station.

42. Apparatus according to claim 41 in which the preconditioning station comprises an electrostatic spray gun for supplying the capture enhancing liquid.

43. Apparatus according to any of claims 27 to 42 comprising an electrode disposed to contact a substrate at the coating station.

44. Apparatus according to claims 43 in which the electrode is a support for the substrate.
45. Apparatus according to claim 44 in which a plurality of the said electrodes form part of a support surface for substrates.
46. Apparatus according to claim 45 in which the support surface is continuous.
47. Apparatus according to claim 45 or 46 in which the support surface is a conveyor disposed between the coating and fusing stations to move the substrate from the coating station to the fusing station.
48. Apparatus according to claim 47 in which the conveyor is also disposed between the fusing and cooling stations to move the substrate from the fusing station to the cooling station.
49. Apparatus according to claim 47 or 48 in which the conveyor is also disposed between the preconditioning and coating stations to move the substrate from the preconditioning station to the coating station.
50. Apparatus according to any of claims 47 to 49 in which the conveyor is the outer surface of a rotating drum having discrete areas electrically isolated from the drum surface for the reception of respective substrates.
51. Apparatus according to claim 50 in which the said areas are depressions in the said surface of the drum.
52. Apparatus according to claim 50 or 51 in which the said areas are each part of a respective moving electrode, each moving electrode extending inside the drum, the drum further comprising a first arcuate stationary electrode so disposed inside the drum

that as one of the said areas passes through the coating station the associated electrode is in electrical contact with the first stationary electrode.

53. Apparatus according to claim 52 in which, in use, the first stationary electrode is, in use, at a potential difference to earth.

54. Apparatus according to claim 52 or 53 further comprising a second arcuate stationary electrode so disposed inside the drum that as one of the said moving electrodes passes through the preconditioning station it is in electrical contact with the second stationary electrode.

55. Apparatus according to claim 54 in which the second stationary electrode is, in use, earthed.

56. Apparatus according to any of claims 50 to 55 comprising a vacuum device for holding the substrates on the surface of the drum.

57. Apparatus according to any of claims 50 to 56 further comprising a second drum and second coating and fusing stations, the second drum being so disposed relative to the first drum that substrates leaving the first drum with a coated surface are transferred onto the second drum with an uncoated surface exposed.

58. Apparatus according to claim 57 further comprising a second preconditioning station adjacent the second drum.

59. A drum for apparatus according to any of claims 50 to 58.

60. A solid pharmaceutical dosage form having one coated face and one uncoated face.

61. A coated pharmaceutical having one coating on one face and


a different coating on the other face.

62. A coated pharmaceutical the surface of one face of which is two or more adjacent different coatings.

63. A coated pharmaceutical according to claim 61 or 62 in which the coatings are of different colours.

64. A coated pharmaceutical according to claim 61, 62 or 63 in which the coatings contain different polymers.

Fig.1.



2/2

Fig.2.





Fig.3.



INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 96/01102

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B05B5/08 A61K9/28 A61J3/00 B05D1/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B05B A61K A61J B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 307 642 (BEHR INDUSTRIEANLAGEN) 22 March 1989 see column 3, line 58 - column 4, line 44 ---	1,2,4,6, 7,9,10, 12,23, 26-28, 31,34, 42-45
X	DE,A,22 47 701 (HAASE HEINZ DR) 11 April 1974 see claim 1 ---	1,2,4,7, 12,23, 26-28,35
X	US,A,3 900 000 (GALLEN THOMAS J) 19 August 1975 see column 5, line 11 - column 6, line 9 ---	1,2,4,7, 12, 26-28, 31,35
-/--		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

& document member of the same patent family

Date of the actual completion of the international search

28 August 1996

Date of mailing of the international search report

19.09.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Juguet, J

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 96/01102

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,92 14451 (HOECHST UK LTD) 3 September 1992 cited in the application see the whole document	1,13-17, 25-27, 36,39
X	---	61,64
X	EP,A,0 607 009 (MCNEIL 778 INC) 20 July 1994 see column 3, line 11 - line 45	60,61,63
X	--- EP,A,0 567 201 (HAESSLE AB) 27 October 1993 see abstract -----	62

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC1/GB 96/01102

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0307642	22-03-89	DE-U- 8712547	19-11-87
DE-A-2247701	11-04-74	NONE	
US-A-3900000	19-08-75	NONE	
WO-A-9214451	03-09-92	GB-A- 2253164	02-09-92
		AT-T- 126431	15-09-95
		AU-B- 653989	20-10-94
		AU-B- 1208492	15-09-92
		DE-D- 69204127	21-09-95
		DE-T- 69204127	04-04-96
		EP-A- 0526606	10-02-93
		ES-T- 2078036	01-12-95
		HU-A- 66848	30-01-95
		JP-T- 5508337	25-11-93
		PL-A- 296624	02-11-93
		US-A- 5470603	28-11-95
EP-A-0607009	20-07-94	US-A- 5436026	25-07-95
		AU-B- 5313094	21-07-94
		BR-A- 9400088	11-10-94
		CA-A- 2113242	13-07-94
		CN-A- 1092640	28-09-94
		CZ-A- 9400061	12-07-95
		FI-A- 940128	13-07-94
		HU-A- 71020	28-11-95
		JP-A- 7116228	09-05-95
		NO-A- 940099	13-07-94
		NZ-A- 250666	27-02-96
		PL-A- 301860	25-07-94
EP-A-0567201	27-10-93	GB-A- 2189698	04-11-87
		SG-A- 154294	17-03-95
		AR-A- 240250	30-03-90
		AT-T- 140387	15-08-96
		AU-B- 601974	27-09-90
		AU-B- 7191287	05-11-87
		CA-A- 1292693	03-12-91
		CY-A- 1810	20-10-95

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.